


**AS22759/90**

FEDERAL SUPPLY CLASS  
6145

THE ORIGINAL MILITARY SPECIFICATION WAS ADOPTED AS AN SAE STANDARD UNDER THE PROVISIONS OF THE SAE TECHNICAL STANDARDS BOARD (TSB) RULES AND REGULATIONS (TSB 001) PERTAINING TO ACCELERATED ADOPTION OF GOVERNMENT SPECIFICATIONS AND STANDARDS. TSB RULES PROVIDE FOR (A) THE PUBLICATION OF PORTIONS OF UNREVISED GOVERNMENT SPECIFICATIONS AND STANDARDS WITHOUT CONSENSUS VOTING AT THE SAE COMMITTEE LEVEL, AND (B) THE USE OF THE EXISTING GOVERNMENT SPECIFICATION OR STANDARD FORMAT.

UNDER DEPARTMENT OF DEFENSE POLICIES AND PROCEDURES, ANY QUALIFICATION REQUIREMENTS AND ASSOCIATED QUALIFIED PRODUCTS LISTS ARE MANDATORY FOR DOD CONTRACTS. ANY REQUIREMENT RELATING TO QUALIFIED PRODUCTS LISTS (QPL'S) HAS NOT BEEN ADOPTED BY SAE AND IS NOT PART OF THIS SAE TECHNICAL DOCUMENT.

### THIRD ANGLE PROJECTION



**SAE Aerospace**  
An SAE International Group

**AS22759/90**  
SHEET 1 OF 7

**REV.**  
**A**


**Tel: 724-776-4970 (outside USA)**  
**Email: [custsvc@sae.org](mailto:custsvc@sae.org)**

**SAE WEB ADDRESS:** <http://www.sae.org>

ISSUED 2000-06 REVISED PROPOSED DRAFT 2003-04

THE REQUIREMENTS FOR ACQUIRING THE PRODUCT DESCRIBED HEREIN SHALL CONSIST OF THIS SPECIFICATION SHEET AND THE ISSUE OF THE FOLLOWING SPECIFICATION LISTED IN THAT ISSUE OF THE DEPARTMENT OF DEFENSE INDEX OF SPECIFICATIONS AND STANDARDS (DODISS) SPECIFIED IN THE SOLICITATION: MIL-W-22759.

REVISION A IS EDITORIAL ONLY, FOR INSERTION OF THE FOLLOWING STATEMENT. "THIS SPECIFICATION IS NOT INTENDED FOR USE IN NAVAL AIRCRAFT OR NAVAL AIR SYSTEMS APPLICATIONS."



FP - Fluorocarbon Polymer, modified Polytetrafluoroethylene (PTFE)

1/ Alloy Conductor: The size 26 AWG conductor shall be ultra-high strength copper alloy. The breaking strength shall be 21.5 lbs. (min.) and the conductor elongation shall be 6.0% (min). All other gauge sizes shall be high strength copper alloy in accordance with MIL-W-22759

FIGURE 1. GENERAL CONFIGURATION.

TABLE I. CONSTRUCTION DETAILS.

Part No. <sup>1/</sup>	Wire Size	Conductor			Finished Wire			
		Stranding (number of strands x AWG gauge of strands)	Diameter (in.)		Resistance at 20° C (68°F) (ohms/ 1000 ft max.)	Diameter (in.)		Weight (lb./1000 Ft) (Max.)
			MIN.	MAX.		Min.	Max.	
M22759/90-26-*	26	19 x 38	0.0175	0.0204	58.4	0.033	0.037	1.55
M22759/90-24-*	24	19 x 36	0.0225	0.0254	30.1	0.038	0.042	2.15
M22759/90-22-*	22	19 x 34	0.0285	0.0314	18.6	0.043	0.047	3.00
M22759/90-20-*	20	19 x 32	0.0365	0.0404	11.4	0.051	0.055	4.55

<sup>1/</sup> Part Number: The asterisks in the part number column of Table I shall be replaced by color code designators in accordance with MIL-STD-681. Examples: M22759/90-20-93 is a 20 AWG white with orange stripe.

TABLE II. WIRE INSULATION MATERIALS. 1/

Tape Code	Thickness (Nom)	Material
1	0.0020	0.0005 (FP) / 0.0010 (Polyimide) / 0.0005 (FP)
2	0.0020	FP (Unsintered)

<sup>1/</sup> Physical properties of FP unsintered tapes shall be in accordance with MIL-W-22759 requirements.

TABLE III. PHYSICAL PROPERTIES OF FP/POLYIMIDE/FP TAPES.

Tensile Strength	19,000 lb/in sq. (average minimum)
Tensile Modulus	350,000 lb/in sq. (average minimum)
Elongation	40 percent (average minimum)
Dielectric Strength	4,000 volts/mil (average minimum)
0.0005 FP Layer (bottom)	Distinguishable color (next to conductor) May be used at manufacturer's option

TABLE IV. TAPE OVERLAP REQUIREMENTS. 1/

Wire Size	Wrap 1			Wrap 2			Nominal Wall Thickness (mils)
	Tape Code	Percent Overlap		Tape Code	Percent Overlap		
		Min	Max		Min	Max	
26	1	50.5	54.0	2	50.5	54.0	7.4
24	1	50.5	54.0	2	50.5	54.0	7.4
22	1	50.5	54.0	2	50.5	54.0	7.4
20	1	50.5	54.0	2	50.5	54.0	7.4

<sup>1/</sup> Wrap 1 is innermost tape which is in contact with the conductor.

TABLE V. FLUID TABLE.

Test Fluid	Test temperature (°C (°F))	Immersion time (hrs.)
A. MIL-A-8243 Anti - icing and Deicing Defrosting Fluid, undiluted	48 - 50 (118 - 122)	20
B. MIL-A-8243 Anti - icing and Deicing Defrosting Fluid, diluted 60/40 (fluid/water) ratio	48 - 50 (118 - 122)	20
C. MIL-C-43616, Cleaning Compound, Aircraft Surface, Type I	48 - 50 (118 - 122)	20
D. ASTM D1153, Methyl Isobutyl Ketone (For use in Organic Coatings)	20 - 25 (68 - 77)	168
E. SAE AS 1241, Fire Resistant Hydraulic Fluid for Aircraft	48 - 50 (118 - 122)	20
F. MIL-L-7808, Lubricating Oil, Aircraft Turbine Engine, Synthetic Base	118 - 121 (244 - 250)	30
G. MIL-C-87937, Clean Compound, Aerospace Equipment, Type II or Type IV, undiluted	63 - 68 (145 - 154)	20
H. MIL-C-87937, Clean Compound, Aerospace Equipment, Type II or Type IV, diluted 25/75 (fluid/water) ratio	63 - 68 (145 - 154)	20
I. TT-S-735, Standard Test Fluids: Hydrocarbon, Type I	20 - 25 (68 - 77)	168
J. TT-S-735, Standard Test Fluids: Hydrocarbon, Type II	20 - 25 (68 - 77)	168
K. TT-S-735, Standard Test Fluids: Hydrocarbon, Type IV	20 - 25 (68 - 77)	168
L. Dielectric - coolant Fluid Synthetic Silicate Ester Base, Monsanto Coolanol 25 or approved equivalent.	20 - 25 (68 - 77)	168
M. MIL-G-3056, Gasoline, Automotive, Combat	20 - 25 (68 - 77)	168

## RATINGS:

TEMPERATURE RATING: 260°C (500°F) MAXIMUM CONTINUOUS CONDUCTOR TEMPERATURE.

VOLTAGE RATING: 600 VOLTS (RMS.) AT SEA LEVEL

## ADDITIONAL REQUIREMENTS:

WET ARC PROPAGATION RESISTANCE (TEST REQUIRED FOR INITIAL QUALIFICATION ONLY): TEST IN ACCORDANCE WITH MIL-STD-2223 METHOD 3006. MEASURE THE DAMAGE OF THE BUNDLE ALONG THE AXIS. THE WIRE IS ACCEPTABLE IF THE FOLLOWING CRITERIA ARE MET:

1. A MINIMUM OF 67 WIRES PASS THE DIELECTRIC TEST.
2. THREE WIRES OR LESS FAIL THE DIELECTRIC TEST IN ANY ONE BUNDLE.
3. ACTUAL DAMAGE TO THE WIRE IS NOT MORE THAN 3 INCHES IN ANY TEST BUNDLE.

DRY ARC PROPAGATION RESISTANCE (TEST REQUIRED FOR INITIAL QUALIFICATION ONLY): TEST IN ACCORDANCE WITH MIL-STD-2223 METHOD 3007. MEASURE THE DAMAGE OF THE BUNDLE ALONG THE AXIS. THE WIRE IS ACCEPTABLE IF THE FOLLOWING CRITERIA ARE MET:

1. A MINIMUM OF 67 WIRES PASS THE DIELECTRIC TEST.
2. THREE WIRES OR LESS FAIL THE DIELECTRIC TEST IN ANY ONE BUNDLE.
3. ACTUAL DAMAGE TO THE WIRE IS NOT MORE THAN 3 INCHES IN ANY TEST BUNDLE.

BLOCKING: 260°C ± 2°C (500°F ± 3.6°F)

COLOR: IN ACCORDANCE WITH MIL-STD-104, CLASS 1; EXCEPT AS NOTED BELOW. WHITE PREFERRED. CONFORMITY OF COLOR TO THE LIMITS OF MIL-STD-104 SHALL NOT BE REQUIRED AFTER OVEN EXPOSURE.

Munsell color limits for UV laser markable wire

Color	Hue		Value		Chroma	
	From	To	From	To	From	To
Black	2.5RN	2.5RN	7	8.5	N/A	N/A
Blue	5PB	7.5B	7	8	4	6
Green	2.5G	7.5G	7	9	2	6
Red	10RP	5R	7	8	4	6
Yellow	5Y	10Y	8	9	4	6
Brown	2.5YR	7.5R	7	9	2	4
Orange	10R	2.5YR	6	7	8	10
Violet	2.5P	7.5R	7	8	4	8
Gray	Same as Black		Same as Black		Same as Black	

COLOR STRIPING OR BANDING DURABILITY: 125 CYCLES (250 STROKES), 250 GRAMS WEIGHT

CONDUCTOR STRAND ADHESION: NOT REQUIRED

CONTINUOUS LENGTHS: SCHEDULE B

DYNAMIC CUT-THROUGH (TEST REQUIRED FOR INITIAL QUALIFICATION ONLY: TEST IN ACCORDANCE WITH ASTM D 3032, SECTION 22. BLADE SHALL BE THE STANDARD CUTTING BLADE EXCEPT THE CUTTING EDGE RADIUS SHALL BE 0.005 ± 0.001 INCH. MINIMUM AVERAGE DYNAMIC CUT-THROUGH (LBS) SHALL BE AS FOLLOWS:

Wire Size	23±5°C	150±5°C	200±5°C	260±5°C
26	10 lbs.	8 lbs.	6 lbs.	4 lbs.
20	15 lbs.	12 lbs.	10 lbs.	6 lbs.

FLAMMABILITY: TEST IN ACCORDANCE WITH MIL-STD-2223, METHOD 1006, PROCEDURE A.

REQUIREMENTS:

DURATION OF AFTER-FLAME 3 SECONDS (MAX)  
 FLAME TRAVEL 3.0 INCHES (MAX)  
 NO FLAMING OF TISSUE

FORCED HYDROLYSIS: (TEST REQUIRED FOR INITIAL QUALIFICATION ONLY) 2000 HOURS AT 70°C. TEST 5 SAMPLES OF AWG SIZE 20 ONLY IN ACCORDANCE WITH SAE AS4373 METHOD 602. ALL 5 SAMPLES MUST PASS THE DIELECTRIC TEST AS LISTED IN METHOD 602.

HIGH FREQUENCY SPARK TEST: (WHEN USED IN LIEU OF IMPULSE DIELECTRIC TEST) TEST IN ACCORDANCE WITH MIL-STD-2223 METHOD 3008, 5.7 KILOVOLTS (RMS.) TEST 100 PERCENT OF THE WIRE.

HUMIDITY RESISTANCE: AFTER HUMIDITY EXPOSURE WIRE SHALL MEET THE REQUIREMENTS FOR INITIAL INSULATION RESISTANCE.

IDENTIFICATION OF PRODUCT: NOT REQUIRED FOR SIZE 26. COLOR CODE DESIGNATOR NOT REQUIRED.

IDENTIFICATION DURABILITY: 125 CYCLES (250 STROKES), 250 GRAMS WEIGHT.

IMMERSION (TEST REQUIRED FOR INITIAL QUALIFICATION ONLY): TEST IN ACCORDANCE WITH MIL-STD-2223 METHOD 1001 INCLUDING THE ADDITIONAL FLUIDS LISTED IN TABLE V OF THIS SPECIFICATION. USE MANDRELS AND WEIGHTS LISTED IN TABLE VI FOR BEND TESTING. DIELECTRIC TEST, 2500 VOLTS (RMS), 60 HZ. FOR TURBINE FUEL IMMERSION TEST OF MIL-STD-2223, EITHER JP4 OR MIL-T-83133 TYPE JP-8 (NATO TYPE F-34) MAY BE USED.

IMPULSE DIELECTRIC TEST: 8.0 KILOVOLTS (PEAK). TEST 100 PERCENT OF THE WIRE

INSULATION RESISTANCE: 5000 MEGOHMS FOR 1000 FEET (MIN.)

INSULATION STATE OF SINTER: (TEST REQUIRED FOR QUALIFICATION) EVALUATE FP LAYERS WITH A DIFFERENTIAL SCANNING CALORIMETER PER ASTM D 4591.

	Energy to Melt (Joules/gram)
First Heat	Less than 25 J/g

LIFE CYCLE: 500 HOURS AT  $290^{\circ}\text{C} \pm 2^{\circ}\text{C}$  ( $554^{\circ}\text{F} \pm 3.6^{\circ}\text{F}$ ). DIELECTRIC TEST, 2500 VOLTS (RMS), 60 HZ. USE MANDRELS COATED WITH POLYTETRAFLUOROETHYLENE SUCH THAT THE DIAMETER OF THE MANDRELS, AFTER COATING, STILL CONFORM TO THE REQUIRED TEST MANDRELS DIAMETERS OF TABLE VI. AFTER OVEN EXPOSURE, LAYERS SHALL NOT SEPARATE AND OR TAPES SHALL NOT LIFT ALONG THE INSULATION OR AT THE ENDS.

LOW TEMPERATURE (COLD BEND): USE MANDRELS AND WEIGHTS SPECIFIED IN TABLE VI. CHAMBER TEMPERATURE,  $-65^{\circ}\text{C} \pm 2^{\circ}\text{C}$  ( $-85^{\circ}\text{F} \pm 3.6^{\circ}\text{F}$ ). DIELECTRIC TEST, 2500 VOLTS (RMS), 60 HZ.

SHRINKAGE: 0.091 INCH (MAX.) AT  $290^{\circ}\text{C} \pm 2^{\circ}\text{C}$  ( $554^{\circ}\text{F} \pm 3.6^{\circ}\text{F}$ ).

SMOKE:  $260^{\circ}\text{C} \pm 5^{\circ}\text{C}$  ( $500^{\circ}\text{F} \pm 9^{\circ}\text{F}$ ); NO VISIBLE SMOKE.

SOLDERABILITY: NOT REQUIRED. THIS SLASH SHEET IS PRIMARILY INTENDED FOR CRIMP TERMINATIONS. FOR SOLDERABILITY APPLICATIONS USE THE SILVER COATED COPPER VERSION OF THIS SPECIFICATION.

STRIPPABILITY: (GROUP II QUALITY CONFORMANCE TEST). TEST IN ACCORDANCE WITH ASTM D 3032 SECTION 27. THE LENGTH OF THE INSULATION SLUGS SHALL BE 0.25 INCHES. THERE SHALL BE NO EVIDENCE OF INSULATION LEFT ON THE CONDUCTOR WHEN VIEWED WITH THE NAKED EYE. THE STRIP FORCES (LBS.) SHALL BE AS FOLLOWS:

Wire Size	Min. Force	Max. Force
26-20	0.25 lb.	6.0 lbs.

TAPE OVERLAP: IN ACCORDANCE WITH MIL-STD-2223, METHOD 6005.

TENSILE MODULUS: TEST COMPOSITE FILM IN ACCORDANCE WITH ASTM D 882, METHOD A.

THERMAL INDEX:  $260^{\circ}\text{C}$  ( $500^{\circ}\text{F}$ ) MINIMUM FOR 10,000 HOURS (TEST REQUIRED FOR INITIAL QUALIFICATION ONLY). TEST SIZE 20 ONLY IN ACCORDANCE WITH ASTM D 3032, SECTION 14.

THERMAL SHOCK RESISTANCE: OVEN TEMPERATURE,  $260^{\circ}\text{C} \pm 5^{\circ}\text{C}$  ( $500^{\circ}\text{F} \pm 9^{\circ}\text{F}$ ), MAXIMUM CHANGE IN MEASUREMENT, 0.091 INCHES. NO CRACKING.

UV LASER MARKING: (TEST REQUIRED FOR INITIAL QUALIFICATION ONLY) FP MATERIALS SHALL BE FORMULATED IN SUCH A MANNER TO ACHIEVE A 62% MINIMUM CONTRAST LEVEL WHEN MARKED BY AN ULTRAVIOLET (UV) LASER SOURCE OPERATING AT A DELIVERED POWER NOT TO EXCEED 1.5 JOULES/CM<sup>2</sup>. THE CONTRAST LEVEL IS DEFINED AS

$$CL = \frac{(\text{Reflectance of the background insulation} - \text{Reflectance of the laser mark}) \times 100}{\text{Reflectance of the background insulation}}$$

WRAP (MANDREL WRAP): NO CRACKING, NO DIELECTRIC BREAKDOWN. USE MANDRELS SPECIFIED IN TABLE VI. DIELECTRIC TEST, 2500 VOLTS (RMS), 60 HZ.

TABLE VI. TEST MANDREL AND TEST LOAD REQUIREMENTS.

Wire Size (AWG)	Test Mandrel Diameter <sup>u</sup> (inches)			Test Load <sup>u</sup> (lbs)	
	Cold Bend	Life Cycle/Bend Test	Wrap	Cold Bend	Life Cycle/Bend Test
26	1.00	0.375	0.125	3.00	0.50
24	1.00	0.500	0.125	3.00	0.75
22	1.00	0.500	0.125	4.00	1.00
20	1.00	0.500	0.125	4.00	1.50

<sup>u</sup> Tolerance shall be  $\pm 3$  percent of the given values.

#### QUALIFICATION OF WIRE:

FOR QUALIFICATION, A SOURCE IS REQUIRED TO SUBMIT DATA ON QUALITY CONFORMANCE TESTS AND ANY FINISHED WIRE TESTS AS REQUIRED BY THE QUALIFICATION AUTHORIZATION LETTER. ALL OTHER TESTING WILL BE PERFORMED BY THE QUALIFYING ACTIVITY AT THE SOURCE'S EXPENSE.

DUE TO THE EXTENDED TIME PERIOD OVER WHICH THE THERMAL INDEX TEST IS PERFORMED, A SOURCE MAY BECOME QUALIFIED UNDER THIS SPECIFICATION SHEET WHILE THIS TEST IS STILL IN PROGRESS.